

# Purell GC 7260G


## Expanding performance and processability

Purell GC 7260G demonstrates enhanced organoleptic properties, high stiffness for dimensional stability and excellent processability required for caps and closures on sensitive beverages.

This high performance, high density polyethylene grade also contains an additive package that supports thermal stability allowing high conversion rates with improved discoloration resistance.

### LyondellBasell offers

- Reliable supply with backup-plant solutions
- Grades approved by global brand owners
- Broad product portfolio and global reach
- Personalized service with one face to the customer
- Backwards integration of technological innovation



### Benefits of Purell GC 7260G

- Excellent organoleptic profile addressing still mineral water applications
- High fluidity and processability with low warpage
- Improved conversion productivity by enhancing the use of conversion techniques and complex mold designs
- Good rigidity allows opportunities for weight reductions and design differentiation in closures
- Designed for single and or multi-piece closures systems

### Typical properties of Purell GC 7260G

Properties	Method	Unit	Value
Melt Flow Rate (2.16kg, 190°C)	ISO 1133	g/10min	8
Melt Flow Rate (5kg, 190°C)	ISO 1133	g/10min	23
Density	ISO 1183	g/cm <sup>3</sup>	0.960
Charpy impact (-30°C)	ISO 179/1eA	kJ/m <sup>2</sup>	2.5

You can find out more by visiting our website at: [lyondellbasell.com](http://lyondellbasell.com)

Before using a product sold by one of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE) OTHER THAN AS SEPARATELY AGREED BETWEEN THE PARTIES IN WRITING. This product may not be used in the manufacture of any US FDA Class III Medical Device or Health Canada Class IV Medical Device and may not be used in the manufacture of any US FDA Class II Medical Device or Health Canada Class II or Class III Medical Device without the prior written approval by Seller of each specific product or application. Users should review the applicable Material Safety Data Sheet before handling the product.